

## Specifications of 10/20 Bitumen

TEST	UNIT	Requirement	Test Method
PENETRATION@25C°	Mm/0.1	10-20	EN 1426
Softening Point	C°	58-66	EN 1427
Change of Mass	%	0.5	
Flash point	C°	240	EN 22592
Solubility in Trichloroethylene	%(m/m)	99.0	EN 12592
Softening Point after Hardening	C°	60	EN 1427
Resistance to Hardening at 163	C°		EN 12607-1
Retained Penetration (T.F.O.T)	%	58	