

Specifications of 160/220 Bitumen

TEST	UNIT	Requirement	Test Method
PENETRATION@25C°	Mm/0.1	160-220	D5
Softening Point	C°	35-43	D36
Change of Mass	%	1	EN 12607-1
Flash point	C°	220	D92
Solubility in Trichloroethylene	%(m/m)	99.0	D2042
Fraas breaking Point		-15	
Increase the softness point under normal conditions	C°	11	EN 12607-1
Penetration, %		37	EN 12607-1
Special Weight@ 25°C	gr/cm ³	To be reported	EN 12592
Rolling Thin-Film Oven Test			D2872
Permeability index		-1.5	EN 12607-1