

Specifications of 250/330 Bitumen

TEST	UNIT	Requirement	Test Method
PENETRATION@25C°	Mm/0.1	250-330	EN 1426
Softening Point	C°	30-38	EN 1427
Change of Mass	%	1.0	
Flash point	C°	220	EN22592
Solubility in Trichloroethylene	%(m/m)	99.0	EN 12592
Softening Point after Hardening	C°	32	EN 1427
Resistance to Hardening at 163	C°		EN 12607-1
Retained Penetration (T.F.O.T)	%	35	