

## Specifications of 30/45 Bitumen

TEST	UNIT	Requirement	Test Method
PENETRATION@25C°	Mm/0.1	30-45	D5
Softening Point	C°	52-60	D36
Change of Mass	%	0.5	EN 12607-1
Flash point	C°	240	D92
Solubility in Trichloroethylene	%(m/m)	99.0	D2042
Fraas breaking Point,		-5	
Increase the softness point under normal conditions	C°	8	EN 12607-1
Penetration, %		53	EN 12607-1
Special Weight@ 25°C , gr/cm <sup>3</sup>			EN 12592
Rolling Thin-Film Oven Test			D2872
Permeability index		-1.5	EN 12607-1