

Specifications of 60/90 bitumen

TEST	UNIT	Requirment	TestMethod
PENETRATION@25C°	Mm/10	60-90	ASTM D5
Softening Point	C°	40-60	ASTM D36
Ductility@25C°	CM	100	ASTM D113
Loss on heating	Wt%	0.03	ASTM D6
Flash point	C°	230	ASTM D92
Specific Gravity	Gr/cm3	1.00-1.25	ASTM D70
Solubilite in CS2, WT	%	60.1	ASTM D4