

Specifications of 80/100 Bitumen

TEST	UNIT	Requirement	Test Method
PENETRATION@25C°	Mm/10	80-100	ASTM D5
Softening Point	C°	45-52	ASTM D36
Ductility@25 C°	CM	100	ASTM D113
Loss on heating	Wt%	1	ASTM D6
Specific Gravity	Gr/cm ³	0.99	ASTM D70
Flash point	C°	240	ASTM D92
Spot test	-----	NEGATIVE	A.A.S.H.O.T 102
Retained Penetration (T.F.O.T)	%	47	ASTM D5